

Technical data sheet

ALBERDINGK® U 3700

Characteristic:

Aqueous, anionic dispersion of an aliphatic polycarbonate polyurethane without free isocyanate groups.

Specification:

Solids content % 34.5 - 36.5

pH- value 8.0 - 10.0

Viscosity mPas 20 - 200

According to:

ISO 3251
0.5 g weighed quantity at 105°C

ISO 976

ISO 2555, Brookfield RVT
Spindle 1/rpm 50/factor 2

Further typical data*:

Density g/cm³ 1.0 - 1.1

MFFT °C ca. 0

Solvent-free

According to:

ISO 2811-1

Film properties*:

Blocking point °C ca. 130

E-Modulus N/mm² ca. 5.0 ISO 527-1

Ultimate tensile strength N/mm² ca. 18 ISO 527-1

Elongation at break % ca. 600 ISO 527-1

Applications:

For leather base- and topcoats with outstanding hydrolysis stability.

Technical data sheet

ALBERDINGK® U 3700

Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months after delivery date. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly. The product is only preserved for the transport. For a longer storage time, we recommend to add additional preservative. A warranty for the sterility after storage can not be granted. ALBERDINGK BOLEY GmbH assures that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY GmbH. The product should be stirred well before use.

Packaging:

plastic drums (120 kg)
one-way container (approx. 1000 kg)
as bulk in tank cars, by agreement.

Safety:

For further information on product safety please refer to the current safety data sheet.

Notice:

* General information - the values can not be considered as part of the product specification.

Further information:

The product tends to form sedimentation, so it has to be stirred very well before use.